



Kemgard™

Flame Retardant · Smoke Suppressant

**Kemgard 981 Used to Replace Antimony Oxide
Achieve V-0 with Chlorinated FR**

Application Bulletin #2310

Polypropylene

Polypropylene Formulation
62% resin, 27% Clorarez 760, 1% Ba/Cd stabilizer

<i>Flame Retardant</i>	<i>94 UL</i>
<i>10% antimony oxide</i>	<i>VO</i>
<i>5% antimony oxide</i>	<i>VO</i>
<i>5% Kemgard 981</i>	



SHERWIN-WILLIAMS CHEMICALS

Technical Service: 601 Canal Road, Cleveland, OH 44113 USA; Ph#: (216) 566-2944, Fax#: (216) 566-3837
Customer Service: Post Office Box 1028, Coffeyville, KS 67337 USA; Ph#: (620) 251-0072, Fax#: (620) 251-7276

www.kemgard.com