



Kemgard™

Flame Retardant • Smoke Suppressant

Kemgard MZM

Improved Dynamic Stability in Rigid PVC

Application Bulletin #3420

RIGID PVC - STABILITY

Common Ingredients			
Oxyvinyl 240	100	100	100
ATH Huber 9402	8	8	8
Mark 1900 Tin Stabilizer	4	4	4
Halstab 1214 Acid Scavenger	1	1	1
Calcium Stearate	1	1	1
Paraloid K120N	1	1	1
Paraloid K175	1	1	1
Variables			
KG 911C	10		
AOM		10	
KG MZM			10
Dynamic Stability	5:26	7:02	9:30
Time Minutes			

Stability was determined at 205 C and 100 rpm using a Brabender Plasti-Corder Digi-System equipped with Type 6 Roller Blades (3:2 Speed Ratio).



SHERWIN-WILLIAMS CHEMICALS

Technical Service: 601 Canal Road, Cleveland, OH 44113 USA; Ph#: (216) 566-2944, Fax#: (216) 566-3837
Customer Service: Post Office Box 1028, Coffeyville, KS 67337 USA; Ph#: (620) 251-0072, Fax#: (620) 251-7276

www.kemgard.com