



***Kemgard*[®] 911C**

1000 Parkwood Circle
Suite 1000
Atlanta, GA 30339

phone: (678) 247-7300
fax: (678) 247-2797
e-mail: hubermaterials@huber.com

Typical Physical Properties

Composition:	zinc molybdate/magnesium silicate complex
Appearance:	white powder
Specific Gravity	2.8
Oil Absortion (g/100g)	40.5
Median Particle Size (um)	3.3
pH	6.5
Solubility (g/100mL)	0.030
Moisture (%)	0.40
Residue on 325 Mesh Screen, % max.	0.20

Applications

Kemgard[®] 911C is used for flame retardancy and smoke suppression in plastics compounds, including wire and cable jacketing, rigid sheet, calendered film, wallpaper, adhesives and epoxy compounds.

Kemgard[®] 911C is highly recommended for the following polymers:

- PVC
- Nylon
- Epoxy
- Polyolefins

Key Benefits:

- Highly Efficient and Economical
- Promotes Char Formation
- Compatible in both Halogenated and Non-Halogenated Systems
- Helps meet Common Fire/Smoke Test including ASTM E84, E662, D3843, D2863, UL94, UL910 and NFPA 263